#### PAPER • OPEN ACCESS

# Photocatalytic degradation kinetics of unsymmetrical dimethylhydrazine in aqueous solution by $Fe^{3+}$ doped $Bi_2O_3$

To cite this article: J Qi et al 2019 IOP Conf. Ser.: Mater. Sci. Eng. 479 012034

View the article online for updates and enhancements.

# You may also like

- <u>Synthesis of unsymmetrical</u> <u>dimethylhydrazine oxalate from rejected</u> <u>liquid rocket propellant</u> Xiaogang Mu, Jingjing Yang and Youzhi Zhang
- Research Progress on Propellant Wastewater Treatment Methods Ying Li, Yong Shen, Bentao Li et al.
- <u>Numerical Simulation of Propellant</u> <u>Diffusion Considering Chemical Reaction</u> Xiang Zhan, Cunyan Cui, Zelin Zhao et al.





DISCOVER how sustainability intersects with electrochemistry & solid state science research



This content was downloaded from IP address 3.21.104.109 on 03/05/2024 at 21:04

IOP Conf. Series: Materials Science and Engineering 479 (2019) 012034 doi:10.1088/1757-899X/479/1/012034

**IOP** Publishing

# Photocatalytic degradation kinetics of unsymmetrical dimethylhydrazine in aqueous solution by $Fe^{3+}$ doped $Bi_2O_3$

# J Qi<sup>1</sup>, B Zhao, Y Wang, Y Wu, Z L Xu, Z W Hou and J J Yan

China Jiuquan Satellite Launch Centre, Gansu Jiuquan 732750

<sup>1</sup> E-mail: 1050231223@qq.com

Abstract. The Fe<sup>3+</sup> doped Bi<sub>2</sub>O<sub>3</sub> photocatalyst was prepared by sol-gel method. The photocatalytic degradation experiment was carried out using unsymmetrical dimethylhydrazine (UDMH) simulated wastewater as the target pollutant. The results showed that Fe<sup>3+</sup> doping significantly improved the degradation efficiency of UDMH with an optimum doping concentration of 2.0%. The reaction kinetics study indicated that the reaction was heterogeneously catalyzed and the kinetic fitting results were consistent with pseudo first-order reaction kinetics model. According to the results of linear fitting, the kinetic reaction rate constant of  $Fe^{3+}$  doped Bi<sub>2</sub>O<sub>3</sub> (2.0%) was the largest, about 1.9 times as much as that of undoped Bi<sub>2</sub>O<sub>3</sub>. Finally, a possible mechanism was proposed to explain the enhanced photocatalytic activity.

#### 1. Introduction

As a high-energy liquid propellant, unsymmetrical dimethylhydrazine (UDMH) is widely used in missiles and satellite launch vehicles. In the process of production, storage, and use of UDMH, a large amount of wastewater will be produced. Such wastewater is highly toxic and has a wide range of concentration. If directly discharged, the hazardous wastewater will have adverse effects on people and environment. At present, the main treatment methods for UDMH wastewater are physical method, biological method, chemical method, etc. [1-3], all of which have various drawbacks, such as incomplete oxidation, secondary pollution, and equipment corrosion.

Photocatalytic oxidation is a kind of advanced oxidation processes (AOPs), which has the unique advantages of complete oxidation process, fast reaction rate, low cost, and easy operation. Photocatalysis is widely used in the fields of air purification, degradation of organic pollutants, and advanced treatment of water [4-7]. Most of the photocatalysts used for degradation of organic pollutants are semiconductor materials. Bismuth oxide (Bi<sub>2</sub>O<sub>3</sub>), an important metal oxide semiconductor with a wide energy change, has received considerable interests because of its excellent physicochemical properties, good charge mobility, thermal property, and outstanding photoconductivity [8-12]. Due to these remarkable characteristics, Bi<sub>2</sub>O<sub>3</sub> has been considered to be one of the most promising photocatalysts. In this paper, Fe<sup>3+</sup> doped Bi<sub>2</sub>O<sub>3</sub> prepared by sol-gel method [13] was used as photocatalyst, and photocatalytic degradation experiments were carried out using UDMH wastewater as target pollutants.

#### 2. Experiment

All chemicals were of reagent grade and used without further purification. Distilled water was used throughout this experiment.

Content from this work may be used under the terms of the Creative Commons Attribution 3.0 licence. Any further distribution of this work must maintain attribution to the author(s) and the title of the work, journal citation and DOI. Published under licence by IOP Publishing Ltd 1

IOP Conf. Series: Materials Science and Engineering 479 (2019) 012034 doi:10.1088/1757-899X/479/1/012034

# 2.1. Sythesis of $Fe^{3+}$ doped $Bi_2O_3$ photocatalyst

The Fe<sup>3+</sup> doped Bi<sub>2</sub>O<sub>3</sub> photocatalyst was prepared by sol-gel method and the detailed synthesis procedure was as follows: 5.0 g Bi (NO<sub>3</sub>)<sub>3</sub> 5H<sub>2</sub>O was dissolved in 20.0 mL HNO<sub>3</sub> aqueous solution (HNO<sub>3</sub> 3.3 mL, H<sub>2</sub>O 16.7 mL). Then 4.0 mL PEG200, 2.0 g citric acid and 3.5 mL t-Oct-C<sub>6</sub>H<sub>4</sub>-(OCH<sub>2</sub>CH<sub>2</sub>)<sub>x</sub>OH (x=9-10) were added in the above solution. Fe(NO<sub>3</sub>)<sub>3</sub> 9H<sub>2</sub>O was added to obtain the different molar ratio of Fe/Bi (0, 0.5%, 1.0%, 2.0%, 3.0%). The above solution was stirred for 10 h at room temperature. After that, pieces of 50×100 mm<sup>2</sup> quartz glass were dipped into the colloidal sol where they would be kept for 3 min, and then withdrawn at a rate of 4.0 cm/min. These pieces of quartz glass were dried up at 100 °C in a baking oven. At last the samples were annealed at 550 °C with a heating rate of 1 °C/min, and at this temperature 2 h plateau was maintained.

#### 2.2. Photocatalytic activity test

The photocatalytic activity of  $Fe^{3+}$  doped  $Bi_2O_3$  was investigated by degradation of target pollutants UDMH in aqueous solution under UV-light irradiation (Philips, 8 W, wavelength 253.7 nm). The experiment conditions were 20~25 °C in temperature, and 20~30% in humidity. The distance from the UV lamp to the photocatalysts was 10 cm. The samples of UDMH were taken every 20 minutes, which were determined by spectrophotometry (GB18063-2000).

#### 3. Results and Discussion

# 3.1. Influence of $Fe^{3+}$ doping on photocatalytic activity of $Bi_2O_3$

The degradation of UDMH under UV-light was used to test the influence of  $Fe^{3+}$  doping on  $Bi_2O_3$  photocatalytic activity and the results were shown in Figure 1. Obviously, the incorporation of a small amout of  $Fe^{3+}$  resulted in a sharp increase of UDMH degradation efficiency. As the  $Fe^{3+}$  dopoing concentration increased to 2.0%, the doped  $Bi_2O_3$  showed the highest photocatalytic degradation efficiency (about 100%), after which the photodegradation efficiency decreased. Such a phenomenon can be ascribed mainly to the fact that redundant  $Fe^{3+}$  ions could serve as the recombination centers of photogenerated electrons and holes because of the well-known effect of concentration quenching. Generally, the  $Fe^{3+}$  doped  $Bi_2O_3$  exhibited higher photocatalytic activities than the undoped.



Figure 1. The influence of Fe<sup>3+</sup> doping on removal efficiency of UDMH.

**IOP** Publishing

IOP Conf. Series: Materials Science and Engineering 479 (2019) 012034 doi:10.1088/1757-899X/479/1/012034



**Figure 2.** The relationship graph between initial concentration of UDMH ( $C_0$ ) and initial reaction rate ( $r_0$ ).

#### 3.2. Photocatalytic reaction kinetics

In order to investigate the relationship between initial concentration of UDMH ( $C_0$ ) and initial reaction rate ( $r_0$ ), Fe<sup>3+</sup> doped Bi<sub>2</sub>O<sub>3</sub> (Fe/Bi 2.0%) was placed in five different concentrations of UDMH simulated wastewater (100 mg/L, 200 mg/L, 300 mg/L, 400 mg/L, 500 mg/L) for photocatalytic degradation experiments, and the results were shown in Figure 2. Obviously, the initial rate ( $r_0$ ) of photocatalytic degradation increased with the increase of initial concentration ( $C_0$ ). Plot the reciprocal of the initial reaction rate ( $1/r_0$ ) to the reciprocal of the initial concentration ( $1/C_0$ ) and the relationship graph was shown in Figure 3. There was a linear relationship between  $1/C_0$  and  $1/r_0$ , and the relation equation is:

$$\frac{1}{r} = 27.1739 \times \frac{1}{C} + 0.0045 \tag{1}$$

The linear equation indicated that the relationship between the initial reaction rate  $(r_0)$  and the initial concentration  $(C_0)$  were consistent with Langmuir-Hinshelwood (L-H) model.

$$r = -\frac{dC}{dt} = \frac{KK_1C}{1+K_1C} \tag{2}$$

$$\frac{1}{r} = \frac{1}{K} + \frac{1}{KK_1C}$$
(3)

The Langmuir-Hinshelwood equation is the basic kinetic equation describing the heterogeneous catalytic reaction. The experimental results showed that the photocatalytic degradation of UDMH by  $Fe^{3+}$  doped  $Bi_2O_3$  was heterogeneous catalytic reaction, indicating that the reaction was carried out at the interface between photocatalyst and solution under UV-light. Because of the low reactant concentration (C<sub>0</sub>), L-H equation can be simplified to pseudo first-order kinetic equation.

$$\left(1 + \frac{1}{K_1 C}\right) dC = K dt \tag{4}$$

$$\ln\left(\frac{C}{C_0}\right) + K_1(C - C_0) = -KK_1t$$
(5)

$$\ln\left(\frac{C}{C_0}\right) = -KK_1 t = -k_{app}t \tag{6}$$

where  $C_0$  and C are the concentrations of UDMH at times 0 and t, respectively, and  $k_{app}$  (min<sup>-1</sup>) is the apparent reaction rate constant determined from the linear fitting data as shown in Figure 4.



**Figure 3.** The relationship graph between reciprocal of initial concentration  $(1/C_0)$  and reciprocal of initial reaction rate  $(1/r_0)$ .

![](_page_4_Figure_5.jpeg)

Figure 4. Photocatalytic kinetic linear fitting of UDMH.

The results indicated that the reaction kinetics of all the samples were well fitted by the pseudo first-order reaction kinetics model. Clearly, the kinetic reaction rate constant of  $Fe^{3+}$  doped  $Bi_2O_3$  (2.0%) was the largest (0.041 min<sup>-1</sup>), about 1.9 times as much as that of undoped  $Bi_2O_3$  (0.022 min<sup>-1</sup>).

#### 3.3. Possible photocatalytic mechanism

To explain the enhanced photocatalytic activity of the  $Fe^{3+}$  doped  $Bi_2O_3$ , a possible mechanism was proposed that  $Fe^{3+}$  can act as electron scavenger during the photocatalytic reaction. Under UV-light

IOP Publishing

IOP Conf. Series: Materials Science and Engineering 479 (2019) 012034 doi:10.1088/1757-899X/479/1/012034

irradiation, the photogenerated electrons (e<sup>-</sup>) on the valence band are excited to the conduction band, and at the same time, correspondingly photogenerated holes (h<sup>+</sup>) are generated on the valence band. The Fe<sup>3+</sup> ions doped into Bi<sub>2</sub>O<sub>3</sub> would capture the photogenerated electrons and the reduced state of Fe<sup>2+</sup> ions, which are instable ,would participate in the O<sub>2</sub> reduction reaction to form O<sub>2</sub><sup>-•</sup>. In the meantime, the holes in the valance band react with surface hydroxyl group to produce OH•. The photogenerated holes (h<sup>+</sup>), OH•, and O<sub>2</sub><sup>-•</sup> can act as major reactive species due to their strong oxidation property. It can be described as follows:

$$Bi_2O_3 + hv \rightarrow h^+ + e^- \tag{7}$$

$$Fe^{3+} + e^{-} \rightarrow Fe^{2+}$$
 (electron trapping) (8)

$$Fe^{2+} + O_2 \rightarrow Fe^{3+} + O^{2-} \bullet \text{ (electron transfer)}$$
 (9)

$$h^{+} + OH^{-} \to OH^{\bullet}$$
(10)

Therefore, the electron trapping-transfer process caused by  $Fe^{3+}$  in  $Bi_2O_3$  lattice induces an effective charge carriers separation, leading to higher photocatalytic efficiency.

#### 4. Conclusions

In summary, the photocatalyst  $Bi_2O_3$  with different doping concentrations of  $Fe^{3+}$  were synthesized by sol-gel method. The exceptional photocatalytic performance of  $Fe^{3+}$  doped  $Bi_2O_3$  for the degradation of UDMH under UV-light irradiation was superior over that of undoped  $Bi_2O_3$  and the doped  $Bi_2O_3$  with 2.0% of  $Fe^{3+}$  exhibited the highest photodegradation efficiency. The reaction kinetics study showed that the photocatalytic degradation of UDMH by  $Fe^{3+}$  doped  $Bi_2O_3$  was heterogeneous catalytic reaction, indicating that the reaction was carried out at the interface between photocatalyst and solution under UV-light. The reaction kinetics of all the samples were well fitted by the pseudo first-order reaction kinetics model and the kinetic reaction rate constant of  $Fe^{3+}$  doped  $Bi_2O_3$  (2.0%) was the largest (0.041 min<sup>-1</sup>), about 1.9 times as much as that of undoped  $Bi_2O_3$  (0.022 min<sup>-1</sup>). A possible mechanism was proposed that the enhancement of photocatalytic activity was attributed to the electron trapping-transfer process caused by  $Fe^{3+}$ .

#### References

- [1] Mahmood T A, Reza G 2015 Journal of the Taiwan Institute of Chemical Engineer 49 142
- [2] Angaji M T, Ghiaee R 2015 Ultrasonics Sonochemistry 257
- [3] Xu ZL, Zhang L Q, Zhao B 2016 Chinese Journal of Energetic Materials 12 1168
- [4] Fujishima A, Honda K 1972 Nature 238 37
- [5] Bessekhouad Y, Robert D, Weber JV 2005 Catalysis today 101 315
- [6] Hoffmann MR, Martin ST, Choi WY 1995 Chemical Reviews 95 69
- [7] Wang WZ, Lu G, Wang W, et al 2007 *Crystal Growth & Design* 7 1722
- [8] Anthony H, John MT, Zhou WZ, et al. 1988 Journal of Solid State Chemistry 1 126
- [9] Xie JM, Lü XM, Chen M, et al. 2008 Dyes and Pigments 77 43
- [10] Li JZ, Zhong JB, Huang ST, et al. 2013 Journal of Advanced Oxidation Technologies 16 168
- [11] Zhang L, Wang WZ, Yang J, et al. 2006 Applied Catalysis A: General 308 105
- [12] Bessekhouad Y, Robert D, Weber JV 2005 Catalysis today 101 315
- [13] Qin W, Qi J, Wu XH 2014 Vacuum 107 204